



SPS



RESIMAT EC

Peinture murale extra mate très facile à nettoyer

- Ne brille pas après le nettoyage
- Extra mate
- Déperlant
- Excellent pouvoir couvrant
- Résistance au frottement de classe 1

WWW.SPSBV.COM

RESIMAT EC

DESCRIPTION

Peinture murale extra mate très facile à nettoyer, déperlante, à base d'une émulsion alkyde diluable dans l'eau. Effet mat durable, même après nettoyage. Solution idéale pour les bâtiments publics et les espaces salissants, comme la cuisine, la salle de bains et le hall d'entrée. Haut pouvoir couvrant, belle fluidité, pratiquement inodore et perméable à l'air. Résistance au frottement : Classe 1 conforme à la norme EN 13300/ISO 11998. Pour l'intérieur.

UTILISATION RECOMMANDÉE

as a durable and very easily cleanable, even matt finish for interior walls and ceilings. Suitable surfaces include: existing coats of wall paint, cement and plasterwork, concrete, brick, gypsum panelling, etc. Also extremely suitable for painting glass fibre fabric.

SYSTÈME RECOMMANDÉ

General information: The surface must be capable of supporting the paint, completely set, clean, dry, and free from dust or grease. Repair cracks and fissures. Remove and/or repair all loose and unstable coats.

New, untreated substrates - Prime highly absorbent surfaces in their entirety using SPS Stabilising primer. - Thoroughly clean powdery surfaces. Prime with Stabilising primer after allowing to dry. - After drying, apply 2 coats of SPS Resimat EC. Existing intact coats of wall paint - Clean using SPS Paint cleaner. - Apply an intermediate coat of SPS Wall Primer Extra Opaque if necessary. - After drying, apply 2 coats of SPS Resimat EC. Existing, flaking coats of wall paint - Remove loose parts. - Thoroughly wash powdery coats and allow them to dry. - Carry out any repairs. - Prime with SPS Stabilising primer. - After drying, apply 2 coats of SPS Resimat EC. Contamination caused by nicotine, damp, rust or soot - Clean thoroughly using SPS Paint cleaner. - Treat surface/stain with SPS Sealing primer. - After drying, apply 2 coats of SPS Resimat EC. The systems described above apply for the most common types of surface. For specific applications and/or detailed advice, please contact SPS bv.

DONNÉES TECHNIQUES

| | |
|-------------------------------|-----|
| Densité (g/cm ³): | 1.5 |
| Niveau de brillance: | Mat |
| Niveau de brillance à 85°: | 1% |
| Extrait sec en volume: | 43% |

TEMPS DE SÉCHAGE À 20°C/HR 50%

| | |
|--------------|---|
| Au toucher: | 2 |
| Recouvrable: | 6 |

EPAISSEUR DE FILM HUMIDE RECOMMANDÉE

123 µm

EPAISSEUR DE FILM SEC RECOMMANDÉE

53 µm

CONSUMMATION THÉORIQUE

Approx. 8 m²/litre per coat

CONSUMMATION PRATIQUE

The actual coverage depends on the nature and the structure of the surface and the application method.

PRÉPARATION DE SURFACE

PRÉCAUTIONS D'UTILISATION

Stir thoroughly prior to use. The first coat can be diluted with a maximum of 5% water. Apply in 1 or 2 coats using a suitable brush, paint roller or paint sprayer. For optimal cleanability, apply 2 coats. To avoid visible marks, always work wet-on-wet and distribute the paint evenly. Back-roll all overlaps in the same direction. Do not touch up when drying. Very easy to touch up after drying.

APPLICATION & DILUTION: PISTOLET AIRLESS

Nozzle opening: 0.017-0.021"
Pressure: approx. 180 bars
Air pressure: -

APPLICATION & DILUTION: PISTOLET PNEUMATIQUE

Nozzle opening: 0.015-0.019"
Pressure: approx. 125 bars
Air pressure: approx. 1.5 bars

NETTOYAGE DU MATERIEL / ECLABOUSSURES

Optimal cleanability when fully cured after 30 days. The most common types of dirt are easily and effectively removed with clean, lukewarm water, possibly in combination with a mild detergent. Use a sponge or soft, non-abrasive and lint-free cloth (not a microfibre cloth). No special cleaning products are required.

REMARQUES

Le risque éventuel de reprise est plus important avec les teintes foncées du fait de l'absorption de la lumière qui souligne les défauts. Pour éviter ce risque, préférer une application au pistolet.

PH

9.0000

DURÉE DE VIE

Minimum of 12 months in the tightly sealed original packaging in a dry, cool and frost-free place.

Date d'émission: 24/03/2023

Couleurs et conditionnements disponibles: Reportez-vous à la page produit concernée sur www.rust-oleum.eu pour avoir un aperçu des couleurs et des tailles d'emballage actuellement disponibles.

Notion de responsabilité: Les informations communiquées ici sont véridiques et exactes et sont fournies de bonne foi au meilleur de nos connaissances, mais sans garantie. Il est estimé que l'utilisateur se sera assuré lui-même de la compatibilité de nos produits avec son usage particulier. Rust-Oleum Europe ne sera en aucun cas tenue pour responsable quant aux dommages consécutifs ou indirects. Les produits doivent être stockés, manipulés et appliqués conformément aux conditions respectant les recommandations de Rust-Oleum Europe détaillées dans le dernier exemplaire de la fiche technique du produit. Il incombe aux utilisateurs de veiller à disposer de l'exemplaire actuel. Les dernières versions de la fiche technique du produit sont disponibles gratuitement et peuvent être téléchargées sur www.rust-oleum.eu ou sur demande adressée à notre département Service à la clientèle. Rust-Oleum Europe se réserve le droit de modifier les propriétés de ses produits sans avis préalable.

Rust-Oleum Netherlands B.V.
Zilverenberg 16
5234 GM 's-Hertogenbosch
The Netherlands
T : +31 (0) 165 593 636
F : +31 (0) 165 593 600
info@rust-oleum.eu

Tor Coatings Ltd (Rust-Oleum Industrial)
Shadon Way, Portobello Ind. Estate
Birtley, Chester-le-Street
DH3 2RE United Kingdom
T : +44 (0)1914 113 146
F : +44 (0)1914 113 147
info@rust-oleum.eu

Rust-Oleum France S.A.S.
38, av. du Gros Chêne
95322 Herblay
France
T : +33(0) 130 40 00 44
F : +33(0) 130 40 99 80
info@rust-oleum.eu

N.V. Martin Mathys S.A.
Kolenbergstraat 23
3545 Zelem
Belgium
T : +32 (0) 13 460 200
F : +32 (0) 13 460 201
info@rust-oleum.eu



WWW.SPSBV.COM